

RCPLST21E

Low Shrink Temperature
Tubing



2:1
ratio



Product Overview

RCPLST21E is a low cost general purpose polyolefin tubing, designed for commercial applications where a low shrink temperature is an important factor. RCPLST21E tubing will start to shrink at temperatures over 70°C and will fully recover at 95°C

Features & Benefits

- Halogen Free (not self extinguishing).
- Good Chemical and abrasion resistance.
- Low evolution of acidic gasses.

Applications

- Insulation & protection of delicate substrates.
- Used in marine, mass transit, construction and offshore applications to reduce toxicity risks.
- Versatile in Commercial and Industrial sectors for its abrasion resistance and cosmetic appeal.

Additional Information

Material	Polyolefin
Operating Temperature	-55°C to +105°C
Dielectric Strength	20 KV/mm
Installation Temperature	+70°C to +95°C
Specifications	FMVSS 302 RoHS

Standard Colours

Black = 0	
Clear = X	

Part Number	Supplied ID (mm)	Recovered ID (mm)	Recovered Wall Thickness (mm)	Standard Packaging Spools (m)
RCPLST21E-1.2-Colour-SP	1.2	0.6	0.50	150
RCPLST21E-1.6-Colour-SP	1.6	0.8	0.50	150
RCPLST21E-2.4-Colour-SP	2.4	1.2	0.51	150
RCPLST21E-3.2-Colour-SP	3.2	1.6	0.51	150
RCPLST21E-4.8-Colour-SP	4.8	2.4	0.52	75
RCPLST21E-6.4-Colour-SP	6.4	3.2	0.65	75
RCPLST21E-9.5-Colour-SP	9.5	4.8	0.65	75
RCPLST21E-12.7-Colour-SP	12.7	6.4	0.65	50
RCPLST21E-19.1-Colour-SP	19.1	9.5	0.77	30
RCPLST21E-25.4-Colour-SP	25.4	12.7	0.89	30
RCPLST21E-38.1-Colour-SP	38.1	19.1	1.00	30
RCPLST21E-50.0-Colour-SP	50.0	25.4	1.10	30

All of the information on this datasheet, including illustrations, is believed to be reliable. Users however should independently evaluate the suitability of each product for their application. No warranties as to the accuracy or completeness of this information and the company disclaims any liability regarding its use. The only obligations are those in the standards terms and conditions of sales for this product and in no case will there be liability for any incidental, direct or consequential damages arising from the sale, resale, use or misuse of the product. Specifications are subject to change without notice. In addition the company reserves the right to make change in materials or processing, without notification to buyer, which do not affect compliance with any applicable specification.

Tel: +44(0) 1793 616700 • Fax: +44(0) 1793 644304
uksales@is-rayfast.com • export@is-rayfast.com

www.is-rayfast.com

2 Lydiard Fields, Swindon, Wiltshire, SN5 8UB, UK.

